

Pellet

- Service temperature up to 260°C
- Excellent dielectric properties
- Superior creep resistance at high temperatures
- Excellent low temperature toughness

INOFLON® Grade	Process Methods	Melt Flow Rate (g/ 10 min)	Specific Gravity	Melting Point (°C)	Tensile Strength (MPa)	Elongation (%)	Applications
8003	Extrusion, Injection, Compression and Transfer Moulding	2.3	2.15	310	28	300	Tubes, Linings (Pipes/Valves/fittings) and Transfer molded articles
8003HS	Extrusion, Injection, Compression and Transfer Moulding	2.3	2.15	310	28	300	Tubes, Linings (Pipes/Valves/fittings), Transfer molded articles and semiconductor components
8015	Extrusion, Injection and Transfer Moulding	14	2.15	310	25	300	Extruded Tubes, and profile for hoses, Jacketing, Wire and cable insulation
8015HS	Extrusion, Injection and Transfer Moulding	14	2.15	310	25	300	Extruded Tubes, and profile for hoses, Jacketing, Wire and cable insulation, semiconductor applications

HS-is modified grade of 8003 and 8015 with high purity, improved flex life and environmental stress cracking resistance.

Powder

- Excellent chemical resistance
- Outstanding electrostatic characteristics
- Good transparency
- Excellent non-stick performance

INOFLON® Grade	Process Methods	Melt Flow Rate (g/ 10 min)	Particle Size (µm)	Bulk Density (g/l)	Specific Gravity	Melting Point (°C)	Tensile Strength (MPa)	Elongation (%)	Applications
8103	Electrostatic powder spray	2.3	25	500	2.15	310	28	300	Powder coatings for chemical and industrial equipment
8115	Electrostatic powder spray	14	25	500	2.15	310	25	300	Powder coatings for chemical and industrial equipment

Dispersion

- Non-stick properties
- Inert to chemicals and solvents
- Excellent surface release properties
- Excellent weatherability

INOFLON® Grade	Process Methods	Melt Flow Rate (g/ 10 min)	Solid Content (%PFA resin by weight)	%Surfactant content on PFA Solid	Specific Gravity	Average Particle Size (nm)	pH of Dispersion	Melting Point (°C)	Applications
8900	Dipping, Impregnating, Spraying	15	50	6	1.4	170	>9.5	310	Coating and impregnating glass fibre fabrics, metal substrate, woven packing
8910	Dipping, Impregnating, Spraying	2	60	6	1.5	170	>9.5	310	Coating and impregnating glass fibre fabrics, metal substrate, woven packing

Certifications

- ISO 9001:2015
- ISO 14001:2015
- OHSAS 18001:2007
- REACH
- USP CLASS VI
- FDA
- ROHS
- SVHC
- UL
- EC 10 / 2011

INOFLON® is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer resin. INOFLON® can be used in applications duly approved by GFL. Customers who plan to use the word INOFLON® as the trade mark on or relation to their own fluoropolymer parts and other products in any style or combination or in any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoropolymer resin is permitted to claim that their products contain INOFLON® without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and insure that their specific conditions of processing present no health or safety hazards. GFL does not warranty, either expressly or impliedly in respect of use of this information for application of its INOFLON® branded Fluoropolymer resin and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents.